



AF  
2800

PTO/SB/21 (03-03)

Approved for use through 04/30/2003. OMB 0651-0031

U.S. Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

<b>TRANSMITTAL FORM</b> <i>(to be used for all correspondence after initial filing)</i>	Application Number	09/747,779
	Filing Date	December 22, 2000
	First Named Inventor	Kim, Hong Koo
	Art Unit	2814
	Examiner Name	Marcos D. Pizarro Crespo
Total Number of Pages in This Submission	Attorney Docket Number	000939-073311US

Corres. and Mail  
**BOX AF**

ENCLOSURES (Check all that apply)		
<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached <input checked="" type="checkbox"/> Amendment/Reply <input checked="" type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s)  <input type="checkbox"/> Extension of Time Request  <input type="checkbox"/> Express Abandonment Request  <input type="checkbox"/> Information Disclosure Statement  <input type="checkbox"/> Certified Copy of Priority Document(s)  <input type="checkbox"/> Response to Missing Parts/ Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> Petition <input type="checkbox"/> Petition to Convert to a Provisional Application <input type="checkbox"/> Power of Attorney, Revocation Change of Correspondence Address <input type="checkbox"/> Terminal Disclaimer  <input type="checkbox"/> Request for Refund <input type="checkbox"/> CD, Number of CD(s)	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Other Enclosure(s) (please identify below): Return Postcard
Remarks		The Commissioner is authorized to charge any additional fees to Deposit Account 20-1430.

RECEIVED  
MAY 1 2003  
2800 MAIL ROOM

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT	
Firm or Individual	Townsend and Townsend and Crew LLP Steve Y. Cho Reg. No. 44,612
Signature	
Date	4/25/03

CERTIFICATE OF TRANSMISSION/MAILING			
I hereby certify that this correspondence is being facsimile transmitted to the USPTO or deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450 on this date: April 25, 2003			
Typed or printed	Andrea S. Beck		
Signature		Date	4/25/03

This collection of information is required by 37 CFR 1.5. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 12 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450

If you need assistance in completing the form, call 1-800-PTO-9199 (1-800-786-9199) and select option 2.PA 3301316 v1



I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to: Mail Stop AF, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450

On April 25, 2003

TOWNSEND and TOWNSEND and CREW LLP

By: [Signature]

*#17/Response*  
*KE*  
*9/50*  
*5/6/03*  
**AMENDMENT UNDER 37 CFR 1.116  
EXPEDITED PROCEDURE –  
EXAMINING GROUP 2814**

**Attorney Docket No.: 000939-073311US  
Client Ref. No.: P01HA010/US**

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

In re application of:

Hong Koo Kim ✓

Application No.: 09/747,779 ✓

Filed: December 22, 2000 ✓

For: FABRICATION METHOD AND  
STRUCTURE FOR FERROELECTRIC  
NONVOLATILE MEMORY FIELD  
EFFECT TRANSISTOR ✓

Examiner: Marcos D. Pizarro Crespo

**AMENDMENT UNDER 37 CFR 1.116  
EXPEDITED PROCEDURE EXAMINING  
GROUP 2814**

**Mail Stop AF  
Commissioner for Patents  
P.O. Box 1450  
Alexandria, VA 22313-1450**

**RECEIVED  
MAY -1 2003  
TC 2800 MAIL ROOM**

Sir:

In response to the Final Office Action mailed February 25, 2003, please remarks as follows:

**REMARKS**

Claims 1-24 and 26 are pending. No claim has been amended, canceled, or added.

Claims 1, 3-10, and 14-22 were rejected under 35 U.S.C. 103(a) as being unpatentable over Hirai and Kirilin. Applicant respectfully traverses the rejection. Claim 1 is directed to a method for fabricating a non-volatile memory device. The claim recites, "providing a substrate; forming an oxide layer overlying the substrate; forming a buffer

layer overlying the oxide layer; thermally annealing the buffer layer to enhance an alignment of crystallites of the buffer layer; forming a ferroelectric material overlying the substrate; forming a gate layer overlying the ferroelectric material, the gate layer overlying a channel region; and forming a first source/drain region adjacent to a first side of the channel region and a second source/drain region adjacent to a second side of the channel region."

The claimed invention recites "thermally annealing the buffer layer to enhance an alignment of crystallites of the buffer layer." In one embodiment, the buffer layer, e.g., MgO, is annealed for about 30 minutes at a temperature of 800-1,000 Celsius to enhance the alignment of the buffer layer in a highly oriented pattern (page 7, lines 9-16). This facilitates growth of a highly oriented ferroelectric layers on the buffer layer.

Hirai does not disclose or suggest the above recited step of "thermally annealing the buffer layer to enhance an alignment of crystallites of the buffer layer." Hirai heats the substrate having a paraelectric oxide film 5 to form a silicon oxide layer 4 underneath the paraelectric oxide film 5 (col. 7, lines 37-43).

Accordingly, the purpose of heating in Hirai is entirely different than the recited features in the claimed invention. Many process steps that have similar names provide widely different results depending on the intended purposes. For example, there are many different ways to deposit a film on a substrate and disclosing one way does not disclose or suggest another deposition method, particularly if the intended purposes of deposition is different, e.g., forming of gate oxide and oxide isolation structures. Similarly, various etch steps are also performed differently according to their intended purposes, e.g., different bias and source powers may be used, different gas mixtures, and different temperatures.

Applicant respectfully note that the heating step disclosed in Hirai appears to be different than the annealing step described in the present application, reflecting the differences in intended purposes of the two steps. That is, Hirai is performed at a temperature from 650 to 750 Celsius for 5-20 minutes (col. 7, lines 37-43), whereas the annealing step is performed at a temperature of 800-1,000 Celsius for about 30 minutes

according to the disclosed embodiment. Perhaps, it is possible that different parameters (e.g., different temperature range and different duration) than one disclosed in the present embodiment could be used for "thermally annealing the buffer layer to enhance an alignment of crystallites of the buffer layer." However, one would have to appreciate the need for such a step to formulate a different set of parameters for performing the annealing step recited in claim 1. Hirai does not disclose or suggest such an appreciation. Kirin et al does not remedy the deficiency of Hirai. Therefore, claim 1 is allowable at least for the reasons set forth above.

Claim 21 recites, "thermally annealing the second buffer layer to enhance an alignment of crystallites of the second buffer layer." Neither Hirai nor Kirin disclose this recited feature. Therefore, claim 21 is allowable.

Claim 2 was rejected under 35 U.S.C. § 103(a) as being unpatentable over Hirai, Kirin, and Maiti in view of Yamazaki. Applicant respectfully traverses the rejection. Claim 2 depends from claim 1 and is allowable at least for this reason.

Claims 11 and 12 were rejected under 35 U.S.C. § 103(a) as being unpatentable over Hirai, Kirin, Maiti further in view of Van Zant and Evetts et al. (US 5361720). Applicant respectfully traverses the rejection. Claims 11 and 12 depend from claim 1 and are allowable at this for this reason.

Claim 13 was rejected under 35 U.S.C. § 103(a) as being unpatentable over Hirai, Kirin, Maiti, Van Zant, Evetts and Wolf. Applicant respectfully traverses the rejection. Claim 13 depend from claim 1 and are allowable at this for this reason. In addition, there is no motivation to combine Wolf and Hirai. The temperature and duration of annealing are set according to intended purposes. Hirai discloses a heating step for forming a silicon oxide layer and provides no motivation as to desirability of performing this step at 800-1,000 Celsius. Wolf does not remedy this deficiency.


Claims 23 and 24 were rejected under 35 U.S.C. § 103(a) as being unpatentable over Hirai, Kirin, Maiti in view of Iyer. Applicant respectfully traverses the rejection. These claims depend from claim 21 and are allowable at least for this reason.

Claim 26 was rejected under 35 U.S.C. § 103(a) as being unpatentable over Hirai, Kirin, Maiti, and Wolf. Applicant respectfully traverses the rejection. This claim depends from claim 21 and are allowable at least for this reason. In addition, there is no motivation to combine Wolf and Hirai. The temperature and duration of annealing are set according to intended purposes. Hirai discloses a heating step for forming a silicon oxide layer and provides no motivation as to desirability of performing this step at 800-1,000 Celsius. Wolf does not remedy this deficiency.

CONCLUSION

In view of the foregoing, Applicants believe all claims now pending in this Application are in condition for allowance and an action to that end is urged. If the Examiner believes a telephone conference would aid in the prosecution of this case in any way, please call the undersigned at 650-326-2400.

Respectfully submitted,



Steve Y. Cho  
Reg. No. 44,612

TOWNSEND and TOWNSEND and CREW LLP  
Two Embarcadero Center, 8<sup>th</sup> Floor  
San Francisco, California 94111-3834  
Tel: 650-326-2400  
Fax: 415-576-0300  
SYC:syc  
PA 3300545 v1

**VERSION WITH MARKINGS TO SHOW CHANGES MADE**

**IN THE CLAIMS:**

All pending claims are provided below for the Examiner's convenience.

No claim has been amended or canceled or added.

1. A method for fabricating a non-volatile memory device, the method comprising:
  - providing a substrate;
  - forming an oxide layer overlying the substrate;
  - forming a buffer layer overlying the oxide layer;
  - thermally annealing the buffer layer to enhance an alignment of crystallites of the buffer layer;
  - forming a ferroelectric material overlying the substrate;
  - forming a gate layer overlying the ferroelectric material, the gate layer overlying a channel region; and
  - forming a first source/drain region adjacent to a first side of the channel region and a second source/drain region adjacent to a second side of the channel region.
2. The method of claim 1 wherein the channel region is about 1 micron and less.
3. The method of claim 1 wherein the ferroelectric material is a PZT bearing compound.
4. The method of claim 1 wherein the buffer layer is a magnesium bearing compound.
5. The method of claim 1 wherein the buffer layer is a magnesium oxide layer, the magnesium oxide layer being a barrier layer.
6. The method of claim 1 wherein the ferroelectric material has a thickness of less than about 1,000 Angstroms.
7. The method of claim 1 wherein the buffer layer has a thickness ranging from about 7 to 100 nanometers.

8. The method of claim 1 wherein the ferroelectric material has a thickness of about 100 Angstroms and greater.
9. The method of claim 1 wherein the ferroelectric material is PZT.
10. The method of claim 1 wherein the buffer layer is a barrier diffusion layer, the barrier diffusion layer substantially preventing diffusion between the ferroelectric material to the substrate.
11. The method of claim 1 wherein the buffer material is sputtered from a substantially pure magnesium target to form a magnesium oxide layer.
12. The method of claim 11 wherein the sputtering is maintained at a temperature greater than about 400 degrees Celsius or greater than about 500 degrees Celsius.
13. The method of claim 11 wherein the buffer layer is thermally annealed at a temperature of 800-1000 degrees Celsius for about 30 minutes.
14. The method of claim 1 wherein the ferroelectric material is highly oriented.
15. The method of claim 14 wherein the highly oriented material is a polycrystalline film.
16. The method of claim 1 wherein the ferroelectric material is substantially free from an amorphous structure.
17. The method of claim 15 wherein the polycrystalline film has a crystal structure of 100 angstroms and greater.
18. The method of claim 1 wherein the buffer layer is a template to provide an oriented growth of the ferroelectric material.
19. The method of claim 1 wherein the oxide layer is provided by a dry oxidation process comprising an oxygen bearing compound.
20. The method of claim 1 wherein the oxide layer passivates the surface of the substrate to protect the channel region.
21. A method for fabricating a non-volatile memory device, the method comprising:

providing a substrate;  
forming a first buffer layer overlying the substrate;  
forming a second buffer layer overlying the first buffer layer;  
thermally annealing the second buffer layer to enhance an alignment of  
crystallites of the second buffer layer;  
forming a ferroelectric material overlying the substrate;  
forming a gate layer overlying the ferroelectric material, the gate layer  
overlying a channel region; and  
forming first and second doped regions adjacent to first and second ends  
of the channel region.

22. The method of claim 21, wherein the first buffer layer is a gate  
oxide layer, and the second buffer layer is a MgO layer.

23. The method of claim 21, wherein the first buffer layer is an  
amorphous layer, and the second buffer layer is a highly-oriented layer.

24. The method of claim 23, wherein the second buffer layer has a  
thickness of no more than 10 nm.

26. The method of claim 21 wherein the second buffer layer is  
thermally annealed at a temperature of 800-1000 degrees Celsius.